

MULTIPAPER [140 g/m²]

Carta a superficie naturale, fabbricata con il 100% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC 100% C015523
 Il prodotto è Acid Free, con riserva alcalina, a garanzia di lunga conservazione conformemente alla norma ISO 9706.
 Bianco elevato. Superficie liscia. Effetto glossy. Ottima resa in fronte/retro. Ideale per stampa digitale a colori, stampa laser e inkjet, fotocopie di prestigio a colori e b/n.

Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC 100% C015523
 The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706.
 Superior whiteness. Smooth surface. Glossy effect. Excellent performance on front/back. Ideal for digital color printing, laser and inkjet printing, and color photocopies.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Umidità Assoluta Moisture Content	UNI EN 20287 E.d.P.	%		4,5	5,5
Grammatura Grammage	UNI EN ISO 536 I.O. 10 P44 004	g/m ²	140,0	135,8	144,2
Spessore Thickness	UNI EN 20534 I.O. 10 P44 005	microns		130,0	150,0
Grado di Bianco Brightness	UNI 7623 I.O. 10 P44 006	%	113,0	111,5	114,5
C.I.E. Whiteness C.I.E. Whiteness	ISO 11475 I.O. 10 P44 006		165,0	162,0	168,0
Opacità Opacity	UNI 7624 I.O. 10 P44 006	%		92,0	
Ruvidità [Bendtsen] Roughness [Bendtsen]	UNI 7626-2 I.O. 10 P44 007	ml/min		50,0	100,0